

Hess Grade FFF

ISSUE 5/1970
 REVISION 4/2001
 REVIEW 4/2015

PARTICLE SIZE SPECIFICATION GRADE FFF

SIZE		ALLOWABLE PERCENT PASSING
MICRON	U.S. MESH	
106	140	99.5-100
90	170	99.5-100
75	200	94-100
45	325	69-83

TEST METHOD: ASTM C136-06

LOOSE BULK DENSITY GRADE FFF

46 lbs/per cubic foot (ASTM C29)

CHEMICAL ANALYSIS AND PHYSICAL PROPERTIES

Chemical Name: Amorphous Aluminum Silicate

TYPICAL ANALYSIS

- Silicon Dioxide: 76.2%
- Aluminum Oxide: 13.5%
- Ferric Oxide: 1.1%
- Ferrous Oxide: 0.1%
- Sodium Oxide: 1.6%
- Potassium Oxide: 1.8%
- Calcium Oxide: 0.8%
- Titanium Oxide: 0.2%
- Magnesium Oxide: .05%
- Moisture: <1.0%
- Crystalline SiO₂: None Detected

GENERAL PROPERTIES

- Appearance: White powder
- Hardness (MOHS): 6
- pH: 7.2
- Radioactivity: None
- Softening Point: 900 degrees C
- Water Soluble Substances: 0.15%
- Loss on Ignition - 5%
- GE Brightness: 84
- Specific Gravity: 2.35
- Reactivity: Inert
(except in the presence of calcium hydroxide or hydrofluoric acid)

DESCRIPTION

Amorphous (non-crystalline) in structure and composed primarily of aluminum silicate, pumice is a naturally calcined volcanic glass foam consisting of highly vesicular strands permeated with tiny air bubbles. It is these frothy, friable glass vesicles that, when carefully refined to various grades, give pumice its unique and infinitely useful qualities.

GRADE APPLICATIONS

Used for: finish aircraft cockpits, circuit board prep, copper plated panel prep, chrome cleanser, cosmetic exfoliant grit, dental compounds, erasers, glass cleaner, hand soaps, tumbling media, wood finishing.

PACKAGING OPTIONS

- 50 lb sacks (palletted)
- 2000 lb super sacks (palletted)
- Bulk shipped in pneumatic rail car or tractor trailer

DISTRIBUTOR NETWORK

We have stocking distributors in 23 countries on every continent except Antarctica, allowing us to deliver pumice quickly and economically worldwide.



(208) 766-4777 x111 • email: rd@hesspumice.com
www.hesspumice.com

Mining and refining the purest commercial deposit of white pumice on the planet.

